



separation : stabilisation : filtration/drainage : protection

Properties Table



Properties

Tensile strength (kN/m)	MD 5.8 CD 8.0	MD 8.0 CD 8.0
Elongation (%)	MD 50, CD 55	MD 50, CD 50
Cone drop (mm)	35	35
Pore Size (O ₉₀)	100	100
CBR (N)	1000	1200
Permeability (l/m ² /sec)	100	100
Weight (gsm)	90	105

* a smaller pore size reduces the loss of fines through the material

